

# Spectral PLAST Putty for plastics

Two-component putty for plastics

**RELATED PRODUCTS** 

Hardener

Betox 50PC

### **PROPERTIES**

- Very elastic
  - Soft
- · Resistant against chipping
- Excellent adhesion to most plastics (except for PE, PTFE and mixtures thereof)



## Spectral PLAST Technical data sheet 2019-12-12

SUBSTRATES				
Plastics, except for PE, PTFE and mixtures thereof	Degrease, mat with an abrasive needled cloth, degrease again.			
Old paint coatings	Degrease, dry sand P220 ÷ P280, degrease again.			
Steel	Degrease, dry sand P80 ÷ P120, degrease again.			
Galvanised steel	Degrease, matt with an abrasive needled cloth, degrease again.			
Aluminium	Degrease, matt with an abrasive needled cloth, degrease again.			
Two-component acrylic primers	Degrease, dry sand P220 ÷ P280, degrease again.			
UNDER 385	From 30 minutes to 12 h at 20°C: without sanding  Over 12 h: degrease, dry sand P220 ÷ P280, and degrease.			
Caution: The putty should not be applied directly on reactive sealers (wash primers) or one-component acrylic and nitrocellulose products.				
MIXING RATIO				
		Weight ratio		
	Spectral PLAST	100 g		
	HARDENER	2 g		
CONTENT OF VOLATILE ORGANIC COMPOUNDS				
VOC II/B/b limit*	250 g/l			
Actual VOC content	90 g/l			
* For ready to apply mixture compliant with Directive UE 2004/42/CE				
APPLICATION CONDITIONS				
The putty should be applied at a temperature above +10 °C.				
APPLICATION				
	Clean and sand the surface.			
	Degrease with Spectral EXTRA 785 or Spectral PLAST 815.			
	Mix the components thoroughly until obtaining a uniform colour.			
	Observe the required amount of hardener.			
	It is advisable to use a putty dispenser in order to obtain the appropriate component ratio.			
	Apply the putty. Maximum layer thickness: 3 mm.			



### Spectral PLAST Technical data sheet

2019-12-12

		2019-12-12		
	5 ÷ 8 minutes/20 °C			
DRYING TIMES				
	20 °C	60 °C		
	30 ÷ 45 minutes	10 minutes		
CAUTION: Drying times apply to the temperatures of the individual elements.				
DRYING WITH AN INFRARED RADIATOR				
	Distance	Follow the recommendations of the equipment manufacturer.		
	Time depending on the type and power of the lamp	Approximately 5 min.		
SANDING				
	Rough	P120 ÷ P180		
	Finish	P180 ÷ P240		
COLOUR				
Grey				
EQUIPMENT CLEANING				
NC solvent				
STORAGE CONDITIONS				
Store in a dry and cool room, away from sources of fire and heat.  Avoid direct exposure to sunlight.				
SHELF LIFE				
Spectral PLAST	24 months/20 °C			
HARDENER	18 months/20 °C			
SAFETY				
See Safety Data Sheet.				
OTHER INFORMATIONS				

#### OTHER INFORMATIONS

Registration number 000024104

The effectiveness of our systems results from laboratory research and many years of experience. The data contained herein meets the current knowledge about our products and their application potential. We ensure high quality, provided the user follows the instructions and the work is performed in accordance with good workmanship. It is necessary to do a test application of the product due to its potentially different reaction with different materials. We may not be held liable for defects if the final result was affected by factors beyond our control.